EUROPEAN PATENT OFFICE

Patent Abstracts of Japan

PUBLICATION NUMBER

: 07304859

PUBLICATION DATE

: 21-11-95

APPLICATION DATE

: 10-05-94

APPLICATION NUMBER

: 06096021

APPLICANT: JAPAN STEEL WORKS LTD:THE;

INVENTOR: KOYANAGI KUNIHIKO;

INT.CL.

: C08G 63/06

TITLE

PRODUCTION OF HIGH-MOLECULAR WEIGHT POLYLACTIC ACID AND ITS

MOLDING

ABSTRACT :

PURPOSE: To continuously and simply obtain a high-molecular weight polylactic acid

having high quality at a low cost by a screw type extruder using an inexpensive lactic acid

prepolymer as a raw material.

CONSTITUTION: This polylactic acid having ≥10000 weight-average molecular weight is obtained by subjecting a lactic acid prepolymer having 500-5000 weight- average molecular weight to polycondensation reaction while removing water content by heating preferably at 100-220°C, further preferably at 130-180°C under reduced pressure, preferably ≤200mmHg, further preferably ≤100mmHg in a screw type extruder. This molding can be obtained by extruding the polylactic acid from the screw type extruder.

COPYRIGHT: (C)1995,JPO